




GRAVOTECH

by  BRADY




ENGRAVING PARAMETERS

LS100EX 60 W

SUMMARY

PLASTICS >	Gravoply™ Laser	3
	Gravoply™ Ultra	
	Gravoply™ 2	
ACRYLICS >	Gravoglas™ 1	4
	Acrylic	
FLEXIBLE FOILS >	Rubbalase™	5
	Flexilase™	
	Stickalase™	
METALLICS >	Gravolase™ Metallics	6
	Metallex™	
METALS >	Gravoxal™	7
	Alumamark®	
	Durablack®	
	Gravometal™	
PHENOLICS >	Gravostrat™	7
ADA >	Gravotac™ Exterior	7

MACHINE CONFIGURATION



Machine	LS100EX
Source power	60 W
Lens	2"

ENGRAVING EXAMPLES

**RASTER
ENGRAVING**

Raster
Text engraving

**VECTOR
ENGRAVING**

Vector
Line engraving

**VECTOR
CUTTING**

Vector cutting
Cutting

GRAVOPLY™ LASER

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster	0,8 mm	19	100	500	0	No	1
	1,3 mm	23	100	500	0	No	1
	1,6 mm	19	100	500	0	No	1
Vector	0,8 mm	9	100	500	0	No	1
	1,3 mm	9	100	500	0	No	1
	1,6 mm	9	100	500	0	No	1
Vector cutting	0,8 mm	35	50	500	0	Yes	1
	1,3 mm	45	30	500	0	Yes	1
	1,6 mm	45	25	500	0	Yes	1

GRAVOPLY™ ULTRA

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster	0,5 mm	19	100	500	0	No	1
	1,6 mm	19	100	500	0	No	1
	2,4 mm	19	100	500	0	No	1
Vector	0,5 mm	9	100	500	0	No	1
	1,6 mm	9	100	500	0	No	1
	2,4 mm	9	100	500	0	No	1
Vector cutting	0,5 mm	17	40	500	0	Yes	1
	1,6 mm	47	25	500	0	Yes	1
	2,4 mm	47	10	500	0	Yes	1

GRAVOPLY™ 2

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster	-	19	100	500	0	No	1
Vector	-	7	100	500	0	No	1

Gravoply™ 2 is not recommended for laser cutting, which is why no cutting parameters are provided.

ACRYLICS

GRAVOGLAS™ 1

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes	Comments
Raster	1,5 mm	33	90	500	0	No	1	Engraving below
	3 mm	33	90	500	0	No	1	Engraving below
	5 mm	33	90	500	0	No	1	Engraving below
Vector	1,5 mm	10	40	500	0	No	1	Engraving below
	3 mm	10	40	500	0	No	1	Engraving below
	5 mm	10	40	500	0	No	1	Engraving below
Vector cutting	1,5 mm	23	18	500	0	Yes	1	Leave a protection film
	3 mm	47	10	500	0	Yes	1	Leave a protection film
	5 mm	47	6	500	0	Yes	1	Leave a protection film

ACRYLIC

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes	Comments
Raster	3 mm	19	100	500	0	No	1	
	5 mm	19	100	500	0	No	1	
	10 mm	19	100	500	0	No	1	
Vector	3 mm	10	100	500	0	No	1	
	5 mm	10	100	500	0	No	1	
	10 mm	10	100	500	0	No	1	
Vector cutting	3 mm	47	5	500	0	Yes	1	Pin table recommended
	5 mm	47	3	500	0	Yes	1	Pin table recommended
	10 mm	47	0,8	500	0	Yes	1	Pin table recommended

FLEXIBLE FOILS

RUBBALASE™

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster	2,2 mm	60	20	500	0	No	1
Vector cutting	2,2 mm	100	10	500	0	Yes	1
Vector Pnt	2,2 mm	47	10	500	0	Yes	1

FLEXILASE™

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes	Comments
Raster	0,25 mm	18	100	500	0	No	1	Gravogrip use recommended for fixing
Vector	0,25 mm	10	100	500	0	No	1	Gravogrip use recommended for fixing
Vector cutting	0,25 mm	18	35	500	0	Yes	1	Gravogrip use recommended for fixing

STICKALASE™

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes	Comments
Raster	0,09 mm	17	100	500	0	No	1	Gravogrip use recommended for fixing
Vector	0,09 mm	2	35	500	0	No	1	Gravogrip use recommended for fixing
Vector cutting	0,09 mm	4	35	500	0	Yes	1	Gravogrip use recommended for fixing

GRAVOLASE™ METALLICS

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster	0,5 mm	35	100	500	0	No	1
	1,6 mm	35	100	500	0	No	1
Vector	0,5 mm	9	100	500	0	No	1
	1,6 mm	9	100	500	0	No	1
Vector cutting	0,5 mm	30	35	500	0	Yes	1
	1,6 mm	100	25	500	0	Yes	1

METALLEX™

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster	0,5 mm	40	100	500	0	No	1
	0,8 mm	40	100	500	0	No	1
	1,6 mm	40	100	500	0	No	1
	2,4 mm	40	100	500	0	No	1
Vector	0,5 mm	9	100	500	0	No	1
	0,8 mm	9	100	500	0	No	1
	1,6 mm	9	100	500	0	No	1
	2,4 mm	9	100	500	0	No	1

Metallex™ is not recommended for laser cutting, which is why no cutting parameters are provided.

METALS

GRAVOXAL™

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster		100	50	500	0	No	1
Vector		30	100	500	0	No	1

Gravoxal™ is made of anodized aluminum, which makes it impossible to cut with a CO2 laser.

ALUMAMARK®

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster		30	50	500	0	No	1
Vector		10	50	500	0	No	1

DURABLACK®

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster		30	50	500	0	No	1
Vector		16	50	500	0	No	1

GRAVOMETALL™

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster		30	100	500	0	No	1
Vector		20	50	500	0	No	1

Gravometal™ is made of brass, which makes it impossible to be cut with a CO2 laser.

PHENOLICS

GRAVOSTRAT™

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Raster		19	30	500	0	No	1
Vector		10	100	500	0	No	1

Gravostrat™ is not recommended for laser cutting, which is why no cutting parameters are provided.

ADA

GRAVOTAC™ EXTERIOR

Type	Thickness	Power	Speed	DPI (%)	Focus Offset	Air assist	Passes
Vector cutting	0,8 mm	19	37	500	0	Yes	1
	1,6 mm	47	27	500	0	Yes	1
	3,2 mm	47	9	500	0	Yes	1